



Non-destructive Control in Quality Monitoring of Steel Construction

Maksimov AB* and Gadeyev AV

Abstract

This work based on literary data discusses the influence of the process of metal fatigue on the change of coercivity. Experimentation on alternate stress (alternating voltage) has resulted in an increase of defects concentration of a structure: pin-hole defects – vacancies, line defects – relocations, volumetric defects – micro separation. The area of reversible damaging was chosen as a criterion of an uninterrupted operation. According to a linear accumulative damage theory (Ψ) there was chosen an amount equal to ratio a number of strain cycles (n_i) to the totality of strain cycles at the given strain or load amplitude (N_p). It is proposed to consider that in the area of reversible damaging a condition $\Psi = (0,2-0,3)\delta_p$ must be met where δ_p is a homogeneous deformation of a given steel grade. Devices for testing coercive strength and state standards allowing to define mechanical properties of steel to coercivity.

Keywords

Coercivity measurement; Damaging; Metal; Coercive strength; Constructional steel; Tension; Deformation

Introduction

An objective of this work is a statement of need and necessity of definition of mechanical properties and limited operation life of a metal in the operational process with help of coercive strength.

In the operational process, any construction is exposed to constant and alternate loads. In the course of time, alternate loads lead to metal fatigue and eventually to its failure. Metal fatigue resides in the accumulation of defects of the structural condition in the process of alternate loads. Amount and intensity of load, as a rule, are random and unpredictable features. Hence it is possible only approximately to estimate the influence of spurious behaviors on the change of construction steel microstructure. The change leads to its failure. This is true that fatigue failure occurs accidentally without any apparent marks of prior plastic deformation. Strength properties of constructional steels increase a little at the beginning of the process of fatigue testing and then, attaining a maximum, decrease abruptly and a failure occurs. Steel dislocation structure at fatigue changes the same way as at static tension. At the beginning the growth of density of single dislocations occurs. Afterwards, reaching a certain density, single dislocations develop into dislocation walls forming a cell structure. If further deformed, a cell dislocation structure develops

onto a stripe-like one. It is considered [1] that formation of stripe-like structure is the beginning of evolution of irreversible failure rate. The works [2-5] show that the border line between reversible and irreversible failure rate of steel can be estimated at the deformation amounting to 0,15-0,20 of a homogeneous deformation.

Construction metal can operate securely in the area of reversible failure. Admissible operation of metal may be to a certain degree of development of irreversible failure; afterwards further operation may lead to accident unpredictable fracture. Definition of a border line between reversible and irreversible failure and admissible one is achieved by means of researching of microstructure and mechanical properties of samples, cut out of definite places of a construction. As a rule they are the places with the biggest strain.

Affecting the construction in the operational process is in general of stochastic nature. However, operational conditions of any specific construction can be most probably treated as normal, i.e. as a determined system. Consequently metal damage accumulation can be apparently described with a Palmgren-Miner liner model [6]:

$$\sum \frac{n_i}{N_p} = 1 \quad (1)$$

Where n_i is a number of cycles,

N_p Is a number of cycles before failure at a constant amplitude of deformation or strain.

Indeed, if amplitudes of deformation or strain differ greatly (several-fold), the formula (1) doesn't work. Depending on sequence of amplitude values of deformations or strains, the left part of the formula (1) may have more or less anes [7]. According to Novozhilov's theory, it is sufficient to use linear summation rule for failure calculation at nonstationary loading if deformation or strain amplitude changes moderately.

Therefore, value Ψ_i defined according to the formula can be treated as a quantity characteristic of failure relevant at n_i cycle numbers:

$$\Psi_i = \frac{n_i}{N_p} \quad (2)$$

According to the work [2] reversible failure is relevant to a value equal to $(0,2-0,3)\delta_p$ where δ_p is percentage extension at homogeneous deformation. Therefore, the biggest value of reversible failure with account of the formula (2) looks like:

$$\Psi_{\max.0} = (0,2-0,3)\delta_p \quad (3)$$

The Figure 1 shows the change of coercive strength from the failure rate for steel 09Г2 at extension to the fracture.

In that regard appliance of non-destructive testing of steel structure and properties is of practical importance. Coercive strength of a metal is the most sensitive properties to the change of a microstructure. This way, for example, at the extension deformation of constructional steel to (4-5) % coercive strength increases to (50-80) %, in this condition acoustic properties (the speed of elastic waves), electrical resistance increase by (2-5) % [8-10].

Application of steel coercive force for definition of microstructural characteristics and mechanical properties is allowed by a series of

*Corresponding author: Maksimov AB, Kerch State Marine Technological University, Kerch, Russia, E-mail: aleksandrms@yandex.ru

Received: November 11, 2017 Accepted: December 06, 2017 Published: December 11, 2017




Figure 1: Definition of the area of steel failure by value of coercive force.

regulatory documents: «GOST (State Standard) 30415-96. Steel Nondestructive control of mechanical properties and microstructure of metal products by means of a magnetic method», «OST (industry standard) 14-1-184-65, «TU (technical conditions) -14-1016-74» and other.

At present, an instrumental base of devices for coercive force measurement – coercimeter – is presented rather diverse. The major part of coercimeters has an attachable sensor with the size of pole sections 12 × 28 mm. It corresponds to metal magnetization to a depth of up to 5 mm. A Coercimeter КИФМ-1Н has a size of pole sections of 20 × 40 mm, what corresponds to metal magnetization to a depth of up to 10 mm.

Most of coercimeters have an autonomous mode of operation (from mains and from internal batteries). A mass of devices doesn't exceed 2 kilos. It allows to use them not in both laboratory and real-life conditions.

Coercive force is arc wise connected to the flow limit and temporal resistance to fracture [11,12]:

$$\sigma_T = AH_c^2 \tag{4}$$

Where σ_T is steel flow limit, MPa.

$$\sigma_B = BH_c^2 \tag{5}$$

σ_B is temporal resistance to fracture, MPa;

H_c is coercive force A/m;

A and B are coefficients identified empirically which depend on steel chemical properties.

Coercive force is connected to the grain in proportion [13-15]:

$$H_c = H_{c0} + \frac{C}{d^2} \tag{6}$$

Where d is a grain size;

H_c is coercive force a unit crystal;

C is a coefficient depending on a steel type.

For constructional steel the size corresponds the diameter of a ferritic grain.

Conclusion

With references to the performed research and analysis of literary data we may conclude that there is a sufficient theoretical and experimental base for dependence of coercive force on the steel structure. Steel structure determines a complex of mechanical properties. Consequently, the measurement of coercive force of constructional steel allows to monitor the strength and remaining operation life by means of a nondestructive methods.

References

- Maksimov A (2013) Estimation of damage of low-alloy steel during cold plastic deformation. New materials and technologies in metallurgy and mechanical engineering 1: 29-31.
- Rovinsky B, Rybakova L (1965) Stress, strain, and structural changes in technical iron under cyclic plastic deformation. Metals 3: 101-112.
- Maksimov B, Nalyvaychenko TM (1988) The patent for the invention No 1433990 of the USSR. A method of processing of sheet metal. MSA Newsletter 40.
- Maksimov A, Padhaiski S (1983) The change in the magnitude of asperities of the surface with cyclic plastic bending Metal 2: 161-162.
- Maksimov A, Padhaiski S (1986) Determining acceptable limits of change of parameters of deformation hardening treatment heat-treated rolled. Improving the quality of heat-treated rolled. Metallurgy 87-88.
- Potapova L, Yartsev V (2005) Mechanics of materials under complex stress state. M Eng 244.
- Maksimov A (2009) Influence of the degree of deformation at a single binary deformation processing durability of steel / New materials and technologies in metallurgy and mechanical engineering. 2: 83-86.
- Nehotyaschih V, Bezlyudko G (2010) The Use of coercive force for evaluating the technical condition of structures working under pressure / Technical diagnostics and nondestructive testing. 1: 49-53.
- Matyuk V, Kulagin V (2010) Control of structure, mechanical properties and stress state of ferromagnetically methods of marzitelli / non-destructive testing and diagnostics. 3: 4-14.
- Bida G, Nichipuruk A (2000) Coarticulatory in non-destructive testing. Defectoscopy. 10: 3-27.
- Maksimov A (2013) Determination of grade of steel bars using coercimeter "FORCE". Tech Diag Nondest Test. 2: 47-49.
- Maksimov A (2013) Correlation of the parameters of the equation of the Petch-Hall with the magnitude of the coercive force in the steel. proceedings of the 21 International conference "Modern methods and means of nondestructive control and technical diagnostics.
- Bida G (2010) Grain Size and correlation strength, plastic and viscous properties with the coercivity ferrite-pearlite steels. Tech Diag Nondest Test. 4: 40-45.
- Bezlyudko G, Muzhytskiy V, Popov B (2002) Assessment of the current state and residual life of mill rolls based on magnetic (coercive force) of the method of nondestructive testing. Nondest Test. 4: 3-9.
- Vakulenko K, Kazak M, Bezlyudko G, Eremenko V, Elkina E (2015) Changes of the coercive force under fatigue testing of samples of steel 40X. Prob Mech Eng 18: 66-71.

Author Affiliation

Kerch State Marine Technological University, Kerch, Russia

Top